

CHARCOAL LIMESTONE

Technical Data Sheet



Charcoal is a medium density, tight grain limestone with soft grey hues that make it highly versatile in design possibilities. It is available in all architectural and flatwork formats, as well as interior and exterior veneer.

SOURCE: North America

Applications




Arch. Elements



Moldings



Tile



Mosaics

Considerations



Freeze Thaw
Vertical



Low Variation



Medium Traffic

Technical Data

ASTM 97 Density	ASTM 97 Absorption	ASTM C170 Compressive Strength	ASTM C880 Flexural Strength	ASTM 353 Abrasion Resistance
142.6 lbs/ft ³	4.91%	4,650 (lbs/in ²) wet	920 (lbs/in ²) wet	7.0 low

Care and Maintenance:

- High Acid Sensitivity is a property of limestone. Care must be taken in the presence of acidic foods and cleaning products.
- Low Abrasion Resistance is inherent in most limestone. Light Scratching will occur with exposure to abrasives. A patina will result over time. It is recommended to use mats at entrances in flooring applications.
- This limestone has a medium or moderate absorption rate. It is recommended to seal this material with a high quality penetrating sealer, prior to use. Sealers allow for additional time to "clean up" the spill, before it has time to result in a stain.