

MONTCLAIR MARBLE

Technical Data Sheet



Montclair is one of the oldest quarried marbles in the U.S. With soft green/gray veins, medium color range, and wide variety of finishes available, this stone is highly versatile in interior and exterior applications.

SOURCE: North America


Applications



Arch. Elements



Moldings



Tile



Mosaics

Considerations



Freeze Thaw



Salt Water



Med Variation



High Traffic

Technical Data

ASTM 97 Density	ASTM 97 Absorption	ASTM C170 Compressive Strength	ASTM C880 Flexural Strength	ASTM 353 Abrasion Resistance
169.4 lbs/ft ³	0.1%	10,090 (lbs/in ²) wet	1,410 (lbs/in ²) wet	16.1

Care and Maintenance:

- High acid sensitivity is a property of marble. Care must be taken in the presence of acidic foods and cleaning products.
- Low abrasion resistance is inherent in most marbles. Light scratching will occur with exposure to abrasives. A patina will result over time. It is recommended to use mats at entrances in flooring applications.
- This marble has a low to moderate absorption rate. It is recommended to seal this material prior to use. Sealers allow for additional time to "clean up" the spill, before it has time to result in a stain.