

PIETRA SERENA SANDSTONE

Technical Data Sheet



A unique sandstone with a blue-grey tone and minimal to no veining.

SOURCE: Italy


Applications




Arch. Elements



Moldings



Tile



Mosaics

Considerations



Freeze Thaw



Salt Water



Low Variation



High Traffic

Technical Data

ASTM 97 Density	ASTM 97 Absorption	ASTM C170 Compressive Strength	ASTM C880 Flexural Strength	ASTM 353 Abrasion Resistance
2519 kg/m ³	na	106 MPa	2 MPa	4.3 mm

Care and Maintenance:

- High acid sensitivity is a property of sandstone. Care must be taken in the presence of acidic foods and cleaning products.
- Low abrasion resistance is inherent in most sandstones. Light scratching will occur with exposure to abrasives. A patina will result over time. It is recommended to use mats at entrances in flooring applications.
- This sandstone has a low to moderate absorption rate. It is recommended to seal this material prior to use. Sealers allow for additional time to "clean up" the spill, before it has time to result in a stain.