

# CALACATTA LINCOLN MARBLE

## Technical Data Sheet



Calacatta Lincoln was used at the Lincoln Monument (where this stone gets its name). This marble is quarried deep in the Rocky Mountains in Colorado. We're proud to carry a North American marble with such a storied past.

SOURCE: North America


### Applications




Arch. Elements



Moldings



Tile



Mosaics

### Considerations



Freeze Thaw



Salt Water



Low Variation



High Traffic

### Technical Data

ASTM 97 Density	ASTM 97 Absorption	ASTM C170 Compressive Strength	ASTM C880 Flexural Strength	ASTM 353 Abrasion Resistance
NA	0.14%	55.05 MPa	7.7 MPa	11.25

#### Care and Maintenance:

- High acid sensitivity is a property of marble. Care must be taken in the presence of acidic foods and cleaning products.
- Low abrasion resistance is inherent in most marbles. Light scratching will occur with exposure to abrasives. A patina will result over time. It is recommended to use mats at entrances in flooring applications.
- This marble has a low to moderate absorption rate. It is recommended to seal this material prior to use. Sealers allow for additional time to "clean up" the spill, before it has time to result in a stain.